

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 July 2005 (21.07.2005)

PCT

(10) International Publication Number
WO 2005/066401 A1

(51) International Patent Classification⁷:
D01D 4/02, A61L 17/10, 17/04, F41H 5/04

D01F 6/04,

(74) Agent: **BOOTSMA, J., P., C.**; DSM Intellectual Property,
P.O. Box 9, NL-6160 MA Geleen (NL).

(21) International Application Number:
PCT/NL2004/000903

(22) International Filing Date:
23 December 2004 (23.12.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
PCT/NL04/00029 1 January 2004 (01.01.2004) NL

(71) Applicant (for all designated States except US): **DSM IP ASSETS B.V.** [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SIMMELINK, Joseph, Arnold, Paul, Maria** [NL/NL]; Ceciliastraat 15, NL-6137 AH Sittard (NL). **MENCKE, Jacobus, Johannes** [NL/NL]; Ambyerstraat Zuid 45, NL-6226 AV Maastricht (NL). **MARISSEN, Roelof** [NL/NL]; Koningstraat 55, NL-6121 HS Born (NL). **JACOBS, Martinus, Johannes, Nicolaas** [NL/NL]; Justus Van Maurikstraat 4, NL-6416 EH Heerlen (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR MAKING HIGH-PERFORMANCE POLYETHYLENE MULTIFILAMENT YARN

(57) Abstract: The invention relates to a process for making high-performance polyethylene multi-filament yarn comprising the steps of a) making a solution of ultra-high molar mass polyethylene in a solvent; b) spinning of the solution through a spinplate containing at least 5 spinholes into an air-gap to form fluid filaments, while applying a draw ratio DR_{fluid} ; c) cooling the fluid filaments to form solvent-containing gel filaments; d) removing at least partly the solvent from the filaments; and e) drawing the filaments in at least one step before, during and/or after said solvent removing, while applying a draw ratio DR_{solid} of at least 4, wherein in step b) each spinhole comprises a contraction zone of specific dimension and a downstream zone of diameter D_n and length D_n with L_n/D_n of from 0 to at most 25, to result in a draw ratio $DR_{fluid} = DR_{sp} * DR_{ag}$ of at least 150, wherein DR_{sp} is the draw ratio in the spinholes and DR_{ag} is the draw ratio in the air-gap, with DR_{sp} being greater than 1 and DR_{ag} at least 1. The invention further relates to a high-performance polyethylene multifilament yarn, and to semi-finished or end-use products containing said yarn, especially to ropes and ballistic-resistant composites.



WO 2005/066401 A1